

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 63-146901
(43)Date of publication of application : 18.06.1988

(51)Int.Cl. C08F 2/32

(21)Application number : 61-293494	(71)Applicant : SHIRAISHI CHUO KENKYUSHO:KK TANIGAKI TEIICHI
(22)Date of filing : 11.12.1986	(72)Inventor : TSUKISAKA RYOGO TANIGAKI TEIICHI NUKUI TOKUZO MORITA HISAAKI

(54) REVERSED PHASE SUSPENSION POLYMERIZATION

(57)Abstract:

PURPOSE: To produce a water-soluble or hydrophilic spherical resin having readily adjustable particle sizes and particle distribution, by the reversed phase suspension polymerization of a water-soluble monomer aq. soln. using an organic bentonite as a suspension stabilizer.

CONSTITUTION: A water-soluble monomer aq. soln. (preferably an aq. soln. contg. an ethylenic unsatd. carboxylic acid, etc.) contg. a water-soluble crosslinking agent (e.g., N,N'-methylenebisacrylamide) and a water-soluble polymn. initiator [e.g., potassium persulfate or azobis-(4-cyanopentanoic acid)] is polymerized in a reversed phase suspension using a hydrophobic organic solvent (e.g., an aliphatic hydrocarbon or a halogenated hydrocarbon) usually at a ratio of the solvent: the water-soluble monomer aq. soln. of 1:0.1W1:5 in the presence of an organic bentonite as a suspension stabilizer to form a water-soluble or hydrophilic spherical resin. The bentonite is produced, e.g., by treating a smectite-contg. clay with a sulfonium salt type cationic surfactant, etc.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office